



1101 McKinley Street Anoka, MN 55303 Phone (763) 786-6682 Fax (763) 786-2167 www.polycam.com







The Poly-Cam Female Header Fitting (Series 799) is a barbed mechanical design fitting which is hydraulically compressed into the polyethylene or pipe quality copolymer material. The fitting is fused onto the HDPE blind flange and includes a compression ring for reinforcement.

## <u>Design</u>

Relaxation of the pipe creates a seal to prevent leakage. Under pressure, the internal pressure within the pipe increases the sealing surface area on the barb. Under zero internal pressure, the compression and tensional strain created by the compression of the multi-level barbs are greater than the stress created by relaxation and/or thermal expansion and contraction. As the internal pressure increases, the connection between the pipe material and transition fitting increases.

- Sizes range from .5 to 2" NPT.
- All National Pipe Threads are made to ANSI/ASME B1.20.1 2013.

## System Performance

The transition fitting is designed to handle the pressure rating of the HDPE pipe with a 2:1 safety factor at 73.40 degrees Fahrenheit with a minimum 50-year design life.

## **Quality Assurance**

The transition fitting shall be manufactured by Poly-Cam, Inc. Poly-Cam, Inc. shall provide quality assurance with regards to proper installation, compatibility, performance, and acceptance. The transition joint meets or exceeds the requirements of:

- ASTM 1598 and ASTM 1599
- All fittings meet ARRA requirements.

## **Installation**

**HDPE pipe end:** Install transition fitting to comply with the pipe manufacturer's recommended procedures. All field welds shall be completed per Plastic Pipe Institute's welding procedure for butt fusion.

**Threaded Fitting**: When installing the transition fitting:

- Always use pipe joint sealant or Teflon tape.
- Always use only smooth-jawed or Poly-Cam wrench
- Do not use a pipe wrench.
- Always use 2 wrenches when connecting.
- Over tightening may cause ovality or damage.
- Always pressure test for leaks before backfilling.
- Backfill and compact carefully around transition and service line to prevent ground shifts which could damage the valve and/or transition fitting.

## <u>Material</u>

## **Steel Fitting:**

• Manufactured of Type 304 or Type 316 Stainless Steel (ASTM A249 or ASTM A269), or C954 grade Aluminum Bronze (lead-free material).

## High-Density Polyethylene: HDPE pipe

- Meets ASTM D-3350 with minimum cell classification values of 345464C (PE 3408), PE445574C (PE 4710)
- Meets ASTM F714.
- Density shall be no less than 0.955 g/cm as referenced in ASTM D1505
- Melt index no greater than 0.15 g/10 minutes when tested per ASTM D 1238
- Tensile Strength at Yield –tensile shall be 3,200 psi to less than 3,500 psi as referenced in ASTM D638
- ESCR-Environmental Stress Crack Resistance shall be over 5,000 hours with zero failures when tested per ASTM D 1693-Condition C
- All pipe meets ASTM 3035.
- All certifications will be submitted upon request.

## <u>Warranty</u>

The warranty period is one year after the date of substantial completion of installation.

# Series 517 HDPE Blind Flange with Female NPT

Nominal Size (In.)	Flange O.D. <b>A</b>	Female Thread Outlet Nominal Size <b>B</b>	Thickness <b>T</b>	# of Bolts	Bolt Hole Diameter
2	6	0.5-0.75	1"/2"	4	0.75
3	7.5	0.5-1	1"/2"	4	0.75
4	9	0.5-1.66	1"/2"	4	0.75
6	11	0.5-2.375	1"/2"	8	0.88
8	13.5	0.5-2.375	1"/2"	8	0.88
10	16	0.5-2.375	1"/2"	12	1
12	19	0.5-2.375	1"/2"	12	1
14	21	0.5-2.375	1"/2"	12	1.13
16	23.5	0.5-2.375	1"/2"	16	1.13
18	25	0.5-2.375	1"/2"	16	1.25
20	27.5	0.5-2.375	1"/2"	20	1.25
22	29.5	0.5-2.375	1"/2"	20	1.38
24	32	0.5-2.375	1"/2"	20	1.38

